

Technical Data Sheet



Product name: EasyCork™

Date of issue: 1 November 2016

Version: v1

EasyCork™ is a lightweight cork-filled PLA-based filament which is gravimetrically filled with approximately 30% cork fibres. The gravimetric filling with relatively lightweight cork fibres means that EasyCork™ has extremely high volumetric cork filling properties, allowing you to 3D print beautiful objects with great cork-like aesthetics and cork-like properties such as being lightweight and impact resistant. EasyCork™ has an excellent filament flowing behaviour allowing you to 3D print cork-like objects with high printing speeds. Certain geometric shapes can even be 3D printed with extremely high speeds.

Properties	Typical value	Test Method	Test condition
Physical			
Specific gravity	± 1.10 g/cc	ISO 1183	-
Melt flow rate	n.d.	ISO 1133	260° C/5Kg
Water absorption	-	-	-
Moisture absorption	-	-	-
Mechanical			
Impact strength	5-6 KJ/m131	ISO 179	Charpy Notched @23° C (73° F)
Tensile strength	19,4 Mpa	ISO 527	@Yield 50mm/min (2 inch/min)
Tensile modulus	1050 Mpa	ISO 527	1mm/min
Elongation at break	15%	ISO 527	@ Break 50mm/min (2 inch/min)
Flexural strength	-	-	-
Flexural modulus	-	-	-
Hardness	-	-	-
Thermal			
Print temperature	± 210 - 260° C	-	-
Melting temperature	± 160° C	-	-
Viscat softening temp.	± 46° C	-	-
Optical			
Haze	-	-	-
Transmittance	-	-	-
Gloss	-	-	-

Product details, certifications and compliance		Diameter	Tolerance	Roundness
HS Code	39169090	1.75mm	± 0.05mm	≥ 95%
REACH compliant	Yes	2.85mm	± 0.10mm	≥ 95%
RoHS certified	Yes			
FDA compliant	No			

Formfutura VOF	CoC: 55502105	Tel: +31 (0)85 002 0881
Groenestraat 215	VAT: NL851741083B01	Email: info@formfutura.com
6531 HH Nijmegen	EORI: NL851741083	Website: www.formfutura.com
The Netherlands		

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the forementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.